

ADLER Pigmofix V



Retardant for glass coating using a paint roller for professional and industrial use

	PRODUCT DESCRIPTION
General	Special mixture of solvents to optimize the processability of the mixture ADLER Pigmopur / ADLER Pigmofix G and ADLER PUR-Härter due to retarded drying, if the back of glasses has to be coated by paint roller.
Application area	 As addition to ADLER Pigmopur 24005 ff for coating the back of glass elements, whose edges are protected from direct contact with wetness due to the construction (e.g. wood frames), by using a paint roller. Does not influence the surface quality of the coating system (chemical and mechanical resistance).
	PROCESSING
Instructions for use	Stir ADLER Pigmofix V 90694 carefully into the hardened paint.
	 Use a paint roller for application (short haired roller – see by- products).
	 Please follow our "Guidelines for glass coating with polyurethane paints – Application by paint roller" as well as the technical data sheet of ADLER Pigmopur 24005 ff.
Mixing ratio	Mixing ratio:
	100 parts of ADLER Pigmopur 24005 ff in the desired colour shade
	+ 5 parts of ADLER Pigmofix G 90699 to the paint
10 - 20 %	+ 10 parts of ADLER DD-Härter 82010
	+ 10 to 20 parts of ADLER Pigmofix V 90694
Pot life of the mixing	8 hours

05-14 ZKL 8118

ADLER-Werk Lackfabrik, A-6130 Schwaz

Fon: 0043/5242/6922-301, Fax: 0043/5242/6922-309, Mail: technical-support@adler-lacke.com

Our instructions for use are based on knowledge available currently and shall guide the purchaser / user to the best of one's knowledge, but, however, must be clarified for the areas of application and processing conditions on a case-to-case basis. The purchaser / user decides about the acceptance and use of the delivered product at his / her won risk, which is why we recommend that a sample piece be prepared to check the acceptability of the product. Our general terms and conditions of sale are otherwise applicable. All previous data sheets are rendered invalid with the issue of this one. Rights reserved for the modification of the container sizes, colour shades and degrees of gloss available.

Cleaning the working equipment	With ADLER DD-Verdünnung (thinner) 80019 or ADLER Waschverdünnung 80077.
	ORDERING INFORMATION
Size of trading unit	400 ml
By-products	ADLER Pigmopur G50 24005 ff ADLER DD-Härter 82010 ADLER DD-Verdünnung 80019 ADLER Pigmofix G 90699 ADLER Clean-Grundreiniger 80056 ADLER Waschverdünnung 80077 Lackroller (paint roller) WL 10 cm 9645 811 Lackroller (paint roller) WL 25 cm 9646 011
	FURTHER DETAILS
Durability / Storage	At least 1 year in the original sealed containers. Cool, but frost-free.
Safety-related information	Please follow the associated safety data sheet! The latest version can be retrieved from the Internet at www.adler-lacke.com .